


PankaDisc

Technical specifications



Uncoated beer mat board



Typical technical values for PankaDisc

Property / Unit	Tolerance					Standards
Grammage, g/m ²	±4%	390	500	600	660	ISO 536
Thickness, µm	±5%	900	1150	1400	1550	ISO 534

On request, PankaDisc is available in thicknesses from 800 µm to 1650 µm

Properties not related to grammage

Property / Unit	Tolerance		Standards
Moisture, %	±1.5	7.0	ISO 287
ISO Brightness C/2°, %		75	ISO 2470
Surface Smoothness, Bendtsen, ml/min		1800	ISO 8791-2
Scott Bond, J/m ²		90	TAPPI 569
Absorbency, s, Top		30	
Absorbency, s, Reverse		30	

For more information contact your local sales representatives or

Pankaboard Oy,
Ruukintie 2
FIN-81750 Pankakoski
Tel. +358 (0) 10 480 600
Fax +358 (0) 10 480 4701

Pankaboard Oy
Sales Office
Ahventie 4 A 28
FI-02170 Espoo, Finland
Tel. +358 (0) 10 480 600
Fax +358 (0) 10 480 4702

www.pankaboard.com

All properties according to Pankaboard measurements.
Test climate 23°C / 50%RH (according to ISO 187). Tolerances based upon 95% confidence limits, apply to reel average.
In order to verify, reel average shall be based on 5 single measurements randomly sampled within the reel. These averages will be for at least 19 of 20 reels within the specification limits.