

PankaPlex High Bulk One side bleached groundwood board

Technical specifications



Typical technical values for PankaPlex High Bulk

Property / Unit	Tolerance								Standards
Grammage, g/m ²	±5%	305	340	380	420	460	500	630	ISO 536
Thickness, µm	±5%	700	800	900	1000	1100	1200	1525	ISO 534
Surface Smoothness, Bendtsen, ml/min		2000	2000	2000	2000	2000	2000	2000	ISO 8791-2

Tailor-made substances can be produced upon request, minimum production volume 20 tonnes

Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
Moisture, %	±1.5	9.0	ISO 287
ISO Brightness C/2°, %, Top	±1.5	76	ISO 2470-1
Scott Bond, J/m ²		100	TAPPI 569
Cobb 180 s top, g/m ²		50	ISO 535
Cobb 180 s reverse, g/m ²		50	ISO 535
pH of Aqueous Extract		7.5 – 10.0	ISO 6588
Alkali Reserve, mol/kg		> 0.4	ISO 10716

➤ **For more information contact your local sales representatives or**

Pankakoski Mill Oy
 Ruukintie 2
 FI-81750 Pankakoski
 Finland
 Tel. +358 (0) 10 480 4600
 Fax. +358 (0) 10 480 4701

www.pankaboard.com

All properties according to Pankakoski Mill measurements tested in manufacturing conditions
 Test climate 23°C / 50%RH (according to ISO 187). Tolerances based upon 95% confidence limits, apply to reel average.
 In order to verify, reel average shall be based on 5 single measurements randomly sampled within the reel. These averages will be for at least 19 of 20 reels within the specification limits.