

Technical specifications



Bleached chemical pulp
Groundwood pulp
Bleached chemical pulp




Coasters



Capsels



Food underlays



Displays & laminates

Typical technical values for PankaDisc

Property / Unit	Tolerance										Standards
Grammage, g/m ²	±4%	275*	305*	345*	375*	390	420	470	560	610	ISO 536
Thickness, µm	±5%	620	700	800	850	900	1000	1150	1400	1550	ISO 534
Surface Smoothness, Bendtsen, ml/min		1500	1500	1600	1600	1600	1800	2000	2000	2000	ISO 8791-2

*Grammage produced upon special request only, minimum production volume 20 tonnes

Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
Moisture, %	± 1.5	8.0	ISO 287
ISO Brightness C/2°, %	± 1.5	75	ISO 2470-1
Scott Bond, J/m ²	> 80	90	TAPPI 569
Absorbency top, s		<30	
Absorbency reverse, s		<30	

Tailor-made substances can be produced upon request, minimum production volume 20 tonnes

> For more information contact your local sales representatives or

Pankakoski Mill Oy
Ruukintie 2
FI-81750 Pankakoski
Finland

Tel. +358 (0) 10 480 4600

www.pankaboard.com

Scan to find your local Pankaboard sales contact

