



### Typical technical values for PankaFrame

Property / Unit	Tolerance							Standards
Grammage, g/m <sup>2</sup>	±5%	380*	445*	590	650	680	710	ISO 536
Thickness, µm	±5%	600	700	900	1040	1100	1200	ISO 534

\* Grammage produced upon special request, minimum production volume 10 tonnes

Tailor-made substances can be produced upon request, minimum production volume 20 tonnes

### Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
Moisture, %	±1.5	7.0	ISO 287
ISO Brightness C/2°, %	±2	88	ISO 2470-1
Scott Bond, J/m <sup>2</sup>	>100	100	TAPPI 569
Smoother surface Smoothness**, Bendtsen, ml/min		1500	ISO 8791-2
Cobb 120 s top, g/m <sup>2</sup>		30	ISO 535
Cobb 120 s reverse, g/m <sup>2</sup>		30	ISO 535
pH of Aqueous Extract		7.5 – 10.0	ISO 6588
Alkali Reserve, ml/kg		>0.4	ISO 10716

\*\* Reverse side in production

PankaFrame complies with the FATG requirements set for Conservation Board

All properties according to Pankakoski Mill measurements tested in manufacturing conditions  
 Test climate 23°C / 50%RH (according to ISO 187). Tolerances based upon 95% confidence limits, apply to reel average.  
 In order to verify, reel average shall be based on 5 single measurements randomly sampled within the reel. These averages will be for at least 19 of 20 reels within the specification limits.

> **For more information contact your local sales representatives or**

Pankakoski Mill Oy  
 Ruukintie 2  
 FI-81750 Pankakoski  
 Finland  
 Tel. +358 (0) 10 480 4600  
 Fax. +358 (0) 10 480 4701

[www.pankaboard.com](http://www.pankaboard.com)