

PankaPlex High Bulk One side bleached groundwood board



Technical specifications



Typical technical values for PankaPlex High Bulk

Property / Unit	Tolerance									Standards
Basic Weight, lb/1000 ft ²	±5%	62.5	69.6	77.8	86.0	94.2	102.4	118.8	129.0	ISO 536
Caliper, pts	±5%	27.6	31.5	35.4	39.4	43.3	47.2	55.1	60.0	ISO 534
Surface Smoothness, Bendtsen, ml/min		2000	2000	2000	2000	2000	2000	2000	2000	ISO 8791-2

Tailor-made substances can be produced upon request, minimum production volume 20 tonnes

Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
Moisture, %	±1.5	9.0	ISO 287
ISO Brightness C/2°, %, Top	±1.5	76	ISO 2470-1
Scott Bond, Lbfft/1000 in ²		48	TAPPI 569
Cobb 180 s top, g/m ²		50	ISO 535
Cobb 180 s reverse, g/m ²		50	ISO 535
pH of Aqueous Extract		7.5 – 10.0	ISO 6588
Alkali Reserve, mol/kg		> 0.4	ISO 10716

➤ For more information contact your local sales representatives or

Pankakoski Mill Oy
 Ruukintie 2
 FI-81750 Pankakoski
 Finland
 Tel. +358 (0) 10 480 4600
 Fax. +358 (0) 10 480 4701

www.pankaboard.com