

## Technical specifications



Bleached chemical pulp  
Groundwood pulp  
Bleached chemical pulp



Coasters



Capsels



Food underlays



Displays & laminates

## Typical technical values for PankaDisc

Property / Unit	Tolerance									Standards
Basic Weight, lb/1000 ft <sup>2</sup>	±4%	62.5 <sup>1</sup>	70.7 <sup>1</sup>	76.8 <sup>1</sup>	79.9	88.1	98.3	118.8	129.0	ISO 536
Caliper, pts	±5%	27.6	31.5	33.5	35.4	39.4	45.3	55.1	61.0	ISO 534
Surface Smoothness, Bendtsen, ml/min		1500	1600	1600	1600	1800	2000	2000	2000	ISO 8791-2

<sup>1</sup>Grammage produced upon special request only, minimum production volume 20 tonnes

## Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
Moisture, %	±1.5	8.0	ISO 287
ISO Brightness C/2°, %	±1.5	75	ISO 2470-1
Scott Bond, Lbfft/1000 in <sup>2</sup>	> 38	43	TAPPI 569
Absorbency top, s		<30	
Absorbency reverse, s		<30	

Tailor-made substances can be produced upon request, minimum production volume 20 tonnes



Available as  
carbon neutral  
on request



For more information contact your  
local sales representatives or

Pankakoski Mill Oy  
Ruukintie 2  
FI-81750 Pankakoski  
Finland

Tel. +358 (0) 10 480 4600

[www.pankaboard.com](http://www.pankaboard.com)

Scan to find your local  
Pankaboard sales contact

