

Technical specifications



Bleached chemical pulp



Picture frames



Rigid boxes
(archival)

Typical technical values for PankaFrame

Property / Unit	Tolerance						Standards
Grammage, g/m ²	±5%	380 ¹	590	650	680 ¹	710	ISO 536
Thickness, µm	±5%	600	900	1040	1100	1200	ISO 534

¹Grammage produced upon special request only, minimum production volume 10 tonnes

Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
Moisture, %	±1.5	7.0	ISO 287
ISO Brightness C/2 ⁰ , %	±2	88	ISO 2470-1
Scott Bond, J/m ²	>90	100	TAPPI 569
Smoother surface Smoothness*, Bendsen, ml/min	< 1800	1500	ISO 8791-2
Cobb 120 s top, g/m ²	< 40	30	ISO 535
Cobb 120 s reverse, g/m ²	< 40	30	ISO 535
pH of Aqueous Extract		7.5 – 10.0	ISO 6588
Alkali Reserve, ml/kg		>0.4	ISO 10716

* Reverse side in production

PankaFrame complies with the FATG requirements set for Conservation Board

Tailor-made substances can be produced upon request, minimum production volume 20 tonnes

➤ For more information contact your local sales representatives or

Pankakoski Mill Oy
Ruukintie 2
FI-81750 Pankakoski
Finland

Tel. +358 (0) 10 480 4600

www.pankaboard.com

Scan to find your local Pankaboard sales contact

