

Technical specifications



Bleached chemical pulp
Groundwood pulp
Bleached chemical pulp



Capseals

Typical technical values for PankaSeal

Property / Unit	Tolerance							Standards
Basic Weight, lb/1000 ft ²	±4%	61.4*	71.7*	75.8 ¹	88.1	94.2	102.4	ISO 536
Caliper, pts	±5%	19.7	24.4	27.6	33.1	35.4	39.4	ISO 534
Moisture, %	±1.5	8.0	8.5	8.5	9.0	9.0	9.0	ISO 287
Surface Smoothness, Bendtsen, ml/min		500	600	700	800	800	900	ISO 7891-2
Bending moment Taber 15° MD, gcm	-15%	275	479	572	768	1006	1122	ISO 2493
Bending moment Taber 15° CD, gcm	-15%	112	195	234	313	391	495	

¹Grammage produced upon special request only, minimum production volume 10 tonnes

*Grammage available only in reels

Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
ISO Brightness C/2°, %	±1.5	75	ISO 2470-1
Scott Bond, Lbfft/1000 in ²	> 52	57	TAPPI 569
Cobb 180 s top, g/m ²	< 70	50	ISO 535
Cobb 180 s reverse, g/m ²	< 70	50	ISO 535

Tailor-made substances can be produced upon request, minimum production volume 20 tonnes



Available as
carbon neutral
on request

For more information contact your
local sales representatives or

Pankakoski Mill Oy
Ruukintie 2
FI-81750 Pankakoski
Finland

Tel. +358 (0) 10 480 4600

www.pankaboard.com

Scan to find your local
Pankaboard sales contact

