

Technical specifications



Bleached chemical pulp
Groundwood pulp
Bleached chemical pulp



Coasters



Capsesals



Food underlays



Displays & laminates

Typical technical values for PankaDisc

Property / Unit	Tolerance										Standards
Grammage, g/m ²	±4%	275*	305*	345*	375*	390	420	470	560	610	ISO 536
Thickness, µm	±5%	620	700	800	850	900	1000	1150	1400	1550	ISO 534
Surface Smoothness, Bendtsen, ml/min		1500	1500	1600	1600	1600	1800	2000	2000	2000	ISO 8791-2

*Grammage produced upon special request only, minimum production volume 20 tonnes

Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
Moisture, %	± 1.5	8.0	ISO 287
ISO Brightness C/2°, %	± 1.5	75	ISO 2470-1
Scott Bond, J/m ²	> 80	90	TAPPI 569
Absorbency top, s		<30	
Absorbency reverse, s		<30	

Tailor-made substances can be produced upon request, minimum production volume 20 tonnes



Available as
carbon neutral
on request



For more information contact your
local sales representatives or

Pankakoski Mill Oy
Ruukintie 2
FI-81750 Pankakoski
Finland

Tel. +358 (0) 10 480 4600

www.pankaboard.com

Scan to find your local
Pankaboard sales contact

